



TECHNICAL DATA

ROTATRIM 80 g/m²

No. 515

ISO 9001

Property	UOM	Standard	Range	Typical Values
Grammage	g/m ²	ISO 536	80.0 ± 3.0	79.8
Caliper	µm	ISO 534	106 ± 3.0	106
TS Roughness Bendtsen	ml/min	ISO 8791-2	220 ± 50	240
WS Roughness Bendtsen	ml/min	ISO 8791-2	220 ± 50	200
Brightness with UV		ISO 2470-2	110.0 ± 1.5	111.1
CIE Whiteness		ISO 11475	161 ± 3.0	160
Opacity	%	ISO 2471	Min 91.5	94.0